


## SunGuard® High Performance

## Neutral 60/40


## Neutral glass for weather that's anything but

SunGuard® HP Neutral 60/40 combines solar control and thermal insulation for a truly all-weather solution. The glass's excellent thermal insulation keeps heat in when it's cold and air conditioning in when it's hot, reducing energy costs throughout the whole year. SunGuard® HP Neutral 60/40 is uniform, predictable glass for unpredictable climates.



| Product Information               |   |  |  |  |  |  |
|-----------------------------------|---|--|--|--|--|--|
| Substrate<br>Base Glass/Thickness | Guardian ExtraClear/4-12 mm                                   |  |  |  |  |  |
| Applications                      | Facades / Windows / Doors / Curtain Walls / Roofs             |  |  |  |  |  |
| Manufacturing options             | Annealed and Heat Treated - Single Product / Laminated / Bent |  |  |  |  |  |
| Recommended Coating Positions     | Surface 2 (double IGU) Surface 2 (triple IGU)                 |  |  |  |  |  |
| Maximum Size                      | <3210x6000mm  |  |  |  |  |  |
| Edge Deletion                     | No, with conditions*  |  |  |  |  |  |
| Glass type                        | Single Silver Coated Glass                                    |  |  |  |  |  |
| Glass functions                   | Solar Control Thermal Insulation                              |  |  |  |  |  |
| Fabrication options               | Must be used in Insulated Glass Unit                          |  |  |  |  |  |
| Appearance                        | Neutral   |  |  |  |  |  |







Double Glazed

Triple Glazed

| Visible light        |  |             |  | Ultraviolet     | Solar Energy    |          |         |             |                  |                     | Thermal<br>Properties |  |  |  |
|----------------------|--|-------------|--|-----------------|-----------------|----------|---------|-------------|------------------|---------------------|-----------------------|--|--|--|
| Transmittance        | Reflec   | Reflectance |  |                 | Transmittance   | Reflec   | ctance  | Absorptance |                  | Shading             | U-Value               |  |  |  |
| Visible<br>(τv %)    | pv % out   | pv % in     | General Color<br>Rendering Index<br>(Ra) | Trans UV(τuv %) | Solar<br>(τe %) | pe % out | pe % in | Solar(αe %) | Solar Factor(g%) | Coefficient<br>(sc) | Ug<br>W/m²·K          |  |  |  |
| Double Glazed: 6-16  | Double Glazed: 6-16-4 SunGuard® High Performance Neutral 60/40 Tempered on Guardian ExtraClear #2, Guardian ExtraClear, 90% Argon fill   |             |  |                 |                 |          |         |             |                  |                     |                       |  |  |  |
| 60                   | 25   | 20          | 93                                       | 32              | 38              | 35       | 37      | 27          | 40               | 0.46                | 1.1                   |  |  |  |
| Triple Glazed: 6-14- | Triple Glazed: 6-14-4-14-4 SunGuard® High Performance Neutral 60/40 Tempered on Guardian ExtraClear #2, Guardian ExtraClear, ClimaGuard Premium2 on Guardian ExtraClear #5, 90% Argon fill |             |  |                 |                 |          |         |             |                  |                     |                       |  |  |  |
| 55                   | 26   | 22          | 93                                       | 19              | 31              | 37       | 38      | 31          | 36               | 0.41                | 0.6                   |  |  |  |

The performance values shown are nominal and subject to variations due to manufacturing tolerances. Spectra-photometric values according to EN 410:2011, EN 673:2011 / Metric.

## www.guardianglass.com

All trademarks noted are owned by, licensed to or used with permission by Guardian Glass.

©2021 Guardian Glass, LLC

19, rue du Puits Romain L-8070 Bertrange Grande-Duchy de Luxembourg Phone: +352 27 86 32 60 e-mail: information@guardian.com

Published Date: 21-Oct-2022

The products in this publication are sold subject to Guardian's standard terms and conditions of sale and any applicable written warranties (available at www.guardianglass.com or from your local Guardian representative upon request). It is the responsibility of the purchaser to confirm that the products are suitable for their intended application in compliance with the applicable laws and regulations. Please contact your local Guardian representative to obtain any applicable handling and fabrication guides and for the most current product information.